

Highly Heat Resistant Chamfering Electrode

ChamferTrode®



ELECTRODE

- Fast, easy chamfering to clear grooves and gaps
- Exothermic coating gives highly precise arc
- Highest arcing voltage of any electrode made
- Designed for use with conventional AC/DC machines



DESCRIPTION:

ChamferTrode is a highly heat-resistant electrode whose special exothermic coating concentrates the force of the arc right at the point of application, yielding a highly efficient metal removing tool. The concentrated force of the arc blasts the unwanted metal from its path, leaving an ideal surface for subsequent operations.

ChamferTrode's exothermic coating has a special formula to provide the highest arcing voltage of any electrode made. This is accomplished by using materials within the coating to intensify temperatures in the arc and form high velocity pressure waves toward the molten metal. This coating has a very high melting point that breaks down slower than the core wire, forming a crate which focuses the pressure to blast the metal away.

TECHNICAL DATA:

Polarity: AC or DCEN (-)

Application: Designed for use with conventional AC/DC welding machines using a standard electrode holder.

Recommended Amperages

Diameter	Amperage
3/32" (2.4mm)	150-250
1/8" (3.2mm)	250-350
5/32" (4.0mm)	300-400
3/16" (4.6mm)	300-500

WELDING PARAMETERS:

1. Mark a chalk line where chamfer is desired.
2. On DC, use straight polarity (EN,-)
3. Point electrode like a lance, in direction of travel, at an angle of not more than 20° with the plane of the work.
4. Push electrode along the line of cut, quickly for a shallow chamfer, more slowly, or with a weaving motion, for a deeper gouge. Maintain contact with the base metal at all times. Avoid back and forth movement.
5. Utilizing the heat and force of the highly concentrated arc, push the molten metal ahead and away. If a deeper gouge is needed, repeat procedure until the required depth has been achieved.

TYPICAL APPLICATIONS:

ChamferTrode is designed for use on cast and malleable iron, low, medium and high carbon steel, alloy steel, stainless steel, manganese steel, and most other metals. It is possible to vee out cracks or remove unwanted metal without dismantling, especially in hard-to-reach spaces where it would be impossible to work with a grinder, tools, or even a cutting torch. It is also excellent for burning (or washing) pitted and rusty surfaces prior to welding, beveling edges in preparation for welding, and forming keyways on shafts prior to final finish milling. ChamferTrode is also used for producing corrugations to prevent slipping and for chamfering blow holes and leaks prior to filling by welding.

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION
N94 W14355 Garwin Mace Drive
Menomonee Falls, WI 53051 USA
Tel.: +1 (800) 558-8524
eutectic.com

EUTECTIC CANADA
428, rue Aimé-Vincent
Vaudreuil-Dorion, Québec
J7V 5V5 Canada
Tel.: +1 (800) 361-9439
eutectic.ca



Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.

Chamf 06/17 © 2008, Eutectic Corporation, ® Reg. T.M., Printed in the U.S.A.